



## Walker Textures Gloss Range

Glass Substrate	Surface Finish	Min.	Max.
3mm Clear Glass	Satin	14	23
3mm Clear Glass	Velour	7.3	10.3
3mm Clear Glass	Opaque	8.2	11.4
6mm Clear Glass	Satinlite	28	42
6mm Clear Glass	Satin	8.5	15.5
6mm Clear Glass	Velour	3.7	5.9
6mm Clear Glass	Opaque	3.2	5.2
10mm Clear Glass	Satin	2.5	9.5
10mm Clear Glass	Velour	1.6	2.8
10mm Clear Glass	Opaque	1.2	2.0
12mm Clear Glass	Satin	4.5	9.5
12mm Clear Glass	Velour	1.4	2.6
12mm Clear Glass	Opaque	0.4	1.4
3mm Starphire Glass	Satinlite	33	47
3mm Starphire Glass	Satin	12.5	19.5
3mm Starphire Glass	Opaque	7.8	10.2
6mm Starphire Glass	Satinlite	28	44
6mm Starphire Glass	Satin	8	15
6mm Starphire Glass	Velour	4.7	6.3
6mm Starphire Glass	Opaque	3	5
10mm Starphire Glass	Satin	4	10
10mm Starphire Glass	Velour	1.8	2.6
10mm Starphire Glass	Opaque	0.5	1.5
12mm Starphire Glass	Satin	4	9
12mm Starphire Glass	Velour	1.4	2.6
12mm Starphire Glass	Opaque	0.7	1.3

Gloss is measured on the etched surface.  
Gloss measurements are taken with a BYK micro-gloss 60° gloss meter.

### Walker Glass Company Ltd.

9551 Ray-Lawson Blvd, Montreal, Qc, Canada H1J 1L5  
514.352.3030 1.888.320.3030 textures@walkerglass.com www.walkerglass.com